

Technical Data Sheet

AW-60

Usage AW-60 emulsion provides water repellency, slip resistance, anti-blocking and abrasion resistance to aqueous coatings, printing inks and over print varnishes.

Description Nonionic paraffin wax emulsion

Physical

Appearance:	Milky white liquid
Emulsifier Charge:	Nonionic
Non-Volatile (%):	Paraffin Hydrocarbon Wax
Brookfield Viscosity (cps):	30 - 70
pH:	8.0 to 9.0
Melting Point (wax content):	60°C
Solids Content:	58 - 60

Recommended storage temperature is 40 to 90 °F. Do not subject product to freezing or extremely high temperatures. Keep container tightly closed to prevent skin formation. Product is stable for at least 3 months.

Manufactured In United States